



Address:
JAMBU PERSHAD & SONS
6275/22 Nicholson Road,
Ambala Cantt, Haryana,
INDIA
Pin: 133001

Email:
sales@japson.com
japsonambala@yahoo.com

Website:
www.japson.com
Phone:
+91-171-4006897

Gouy's Balance Method

Product Image



Description

Apparatus for Measurement of Susceptibility of Paramagnetic Solids by Gouy's Method:

In the Gouy's method of susceptibility measurement, the solid sample in the form of a long cylinder (area of cross section A) is hung from the pan of a balance and is placed such that one end of the sample is between the pole-pieces of the magnet (field H) and the other one is out side the field. The force exerted on the sample by the inhomogeneous magnetic field is obtained by measuring the apparent change (m) in the mass of the sample. The susceptibility χ given by:

$$\chi = 2\Delta mg / AH^2$$

If the sample is in the form of powder, it is filled in a long nonmagnetic tube which is then suspended from the pan of the balance.

The setup consists of the following:

(A) DIGITAL BALANCE:

Capacity : 100gms

Sensitivity : 1 mg.

Beam : Load Cell

Display : LCD Display

Operating : 9v. Adaptor workable on 220v.50Hz.

(b) Sample in the form of a long rod:

Set of samples

(c) Electromagnet:

Pole Pieces : 50mm tapered to 25mm

Mag. Field : 10KG 10mm Air gap

Energizing Coils : Two of approx. 13each

Power : 0- 45Vdc, 5Amp.

(D) Electromagnet Power Supply:

Display :- 3 Digit LED

Operating :- 220v.50Hz.

(e) Gaussmeter

Digital 3 1/2 Digital Display

Range :- 2k - 20KG.

with Hall Probe

The experiment is completed in all respect.

-

Gouy's Balance Method

Catalog No. 101021

Disclaimer

The Products details given on this page are indicative in nature and JAPSON reserves the right to change them without prior notice. Buyer is also requested to re-check the specifications and other features of product at the time of order as product development is a continuous process and minor modifications may be made to design based on latest availability, process and design.